

**PVC RESIN
SPECIFICATION**

TYPE	S-57	May-60	S65	S-67	S-70
Appearance	W.P*	W.P	W.P	W.P	W.P
Inherent Viscosity	0.67-0.72	0.74-0.79	0.85-0.91	0.91-0.95	0.98-1.02
K-Value	56-58	59-61	64-66	66-68	69-71
Particle Size %Retained on 40 Mesh %Retained 200 Mesh	Nil => 85	Nil => 85	Nil => 85	Nil => 85	Nil => 85
Porosity(ML/GR)	0.05-0.2	0.05-0.22	0.1-0.26	0.12-0.28	0.2-0.32
Volatile Matter (Heat Loss)%Max	0.7	0.7	0.7	0.7	0.7
Bulk Density (GR/CC) (Apparent)	0.5-0.62	0.55-0.61	0.46-0.60	0.45-0.57	0.44-0.5
Dark Resin (Per 10 SQ. IN.)	0-10	0-10	0-10		0-10

*W.P: White Powder
Packing: 25Kg Paper Bag